

Provisional Data Sheet

PRODUCT DESCRIPTION

Graphene enhanced primer for highly corrosive environments based on epoxy amine chemistry with aluminium flake.

A high-performance 2-pack primer that offers excellent anti-corrosion properties on properly prepared steel substrates in highly corrosive, harsh environments. Suitable for use as a primer under a wide variety of conventional finishes

PRODUCT INFORMATION

Appearance	Bronze paint
Mix Ratio (by volume)	3:1
Mix Ratio (by weight)	4.28:1
Volume solids (%)	70%
VOC (g/l)	250g/l
Recommended WFT	250 microns / per coat
Recommended DFT	125-150 microns / coat
Number of coats:	1 coat for above water areas 2 coats for underwater (immersed) areas
Application Method:	Brush, Roller, Airless spray
Pot life (23°C):	75 minutes
Touch Dry (10°C):	5 hours
Touch Dry (23°C):	4.5 hours
Hard dry (10°C):	8 hours
Hard Dry (23°C):	6 hours
Induction Period:	None Required
Min. self-overcoating interval:	7 hours
Mixing:	Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.
Airless spray:	Tip Range 0.66-0.79 mm (26-31 thou)
Thinning:	Use a Xylene:Butanol blend (3:1) as necessary to manage viscosity. Maximum thinning 20%.

SURFACE PREPARATION**Newbuild:**

All surfaces to be coated should be clean, dry and free from contamination.

Abrasive blast clean to minimum Sa2

Maintenance and Repair:

Rinse the surface with fresh water to remove loose dirt, growth or any other contamination. Scrape away any loose paint that's in bad condition. Remove corrosion products with grinding or sanding, going down to clean metal. Any bare steel that's left needs to be sanded to help the paint scheme adhere to it. Power grind using 24-36 grit to a uniform, clean and bright metal surface. Remove any residues before application of the new system. Where bare steel has been exposed, the first coat of primer should be applied within 4 hours of surface preparation.

STORAGE

Store in accordance with local regulations. The product should be stored in the original container at room temperature in a dry, well-ventilated location away from direct sunlight. Keep away from incompatible materials and food and drink. Keep the container tightly sealed.

SAFETY

Wear appropriate PPE. Use the minimum quantity of product required for a particular process. Use only in well-ventilated areas. Handle and open the container with care. Keep in the original container or an approved alternative made from a compatible material. Always close containers tightly after removal of the product. Empty containers retain product residue and can be hazardous. Do not re-use the container. Dispose of materials in accordance with local regulations.

You will follow any instructions and all applicable guidelines, laws, regulations, government agency guidelines and best industry practice regarding the use, transport, security, and disposal of the products. All statements and technical information contained in this data sheet are given in good faith and are based on information believed to be reliable, but their accuracy and completeness are not guaranteed, and no representation or warranty (express or implied) is given. Any statements and technical information do not constitute an offer to any person and do not form the basis of any contract. All products are sold subject to Applied Graphene Materials' standard terms and conditions of sale. The user will determine the suitability of the products for their intended use prior to purchase and will assume all risk and liability (to the fullest extent permitted under applicable law) in connection with that purchase and intended use. It is the responsibility of those wishing to sell items made from or using the products to inform other users of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information in this datasheet is under constant review and subject to ongoing modification, however, Applied Graphene Materials shall be under no obligation to notify the user of any modifications made.